



PermaWick Company
3110 PermaWick Drive, Columbus, Indiana 47201
Phone: 812-376-0703 • Fax: 812-372-1410
sales@permaWick.com
www.permaWick.com

An ISO9001 Certified Company
PD SHC326
REV. #1
REV. DATE: March 21, 2016

SHC326 Oil **Enhanced PAO Based Synthetic Lubricant for Sintered Metal Bearings**

DESCRIPTION

SHC326 OIL is an optimized synthetic lubricant that exceeds the performance of typical PAO's. It is formulated to resist oxidation and corrosion while minimizing wear. High viscosity index and low pour point indicate excellent low temperature fluidity (-35°C) while also providing protection at high temperatures (130°C).

SHC 326 OIL is optimized for function as an impregnating fluid for powdered metal bearings, parts and wicks and offers protection and reliability over the widest useful temperature range

PRODUCT FEATURES

- Excellent oxidation resistance and corrosion protection
- Very low evaporation rate
- Good load carrying capacity
- Reduces friction for low-wear rates
- Outstanding film strength

Performance Test	Test Method	Typical
Base oil composition	Infra-Red Scan	Optimized PAO
ISO VG	D2422	68
Density @20°C	D1298	0.850
Color	Visual	yellow
Flash Point, °C	D97	>260
Pour Point, °C	D92	-51
Viscosity, cSt @ 40°C	D445	66.28
Viscosity, cSt @ 100°C	D445	10.35
Viscosity Index	D2270	143.2
Copper Corrosion, 24 hrs. @ 100°C	D130	1a
Rust Protection, 3hrs, 60°C	D665(B)	Pass
Falex pin and vee Block, 320Kg, 15 mins	D3233 (Modified)	Pass
Falex pin and vee Block, lbf.	D3233(b)	1750
Evaporation loss, wt. %, 22hrs, 100°C	D972	0.01
Oxidation Induction Time, mins	D6186	51