



255 East Brown Street, Ste 100, Birmingham, MI 48009

Phone: 248-433-3500 • Fax: 248-433-1824

Email: sales@permawick.com

<http://www.permawick.com>

Product: Vibex HP

Rev Level: 4

Rev Date: February 29, 2016

VIBEX-HP Specification

1. Vibex-HP Spec Details, Part N° PDG-014T and PDG-014P

Test Name	Method	Max	Typical	Min
Density, g/cm ³	ASTM D1298		0.874	
Brookfield Vis, 20 rpm @ 25°C	ASTM D2983	570K	510K	450K
Brookfield Vis, 100 rpm @ 25°C	ASTM D2983	180K	140K	100K
Cone Penetration	ASTM D217	225	200	175
Water Resistance, % spray	ASTM D4049		Pass	
Flash Point, °C	ASTM D92		280	260
Pour Point, °C	ASTM D97		-30	-25
Oil Bleed Out, % weight	IPI 121		<0.1	0.15
Water resistance, 54.5°C (130°F), 22hrs	Internal		Pass	
Operating Temperature, °C		-30	25	60
Pounds/ gallon	Conversion		7.29	

Key characteristic are shown in red font

2. Recommended Temperature Range

-30°C to 60°C

3. Appearance

Colorless Translucent with dispersed red particle

4. Packaging

Net Weight in pail.....16Kg (fills a 5 gallon or 18.92 Litre pail)

Net Weight in tube.....290 grams (fills a 310 ml tube)

5. Label Information

Vibex Part Number

Customer Part Number

Lot Number / Individual Container Number

Date of Manufacture