



**Permawick Company**  
 255 E. Brown Street, Suite 100, Birmingham, MI 48009  
 Phone: 248-433-3500 • Fax: 248-594-3433  
 sales@permawick.com  
 www.permawick.com

**An ISO9001 Certified Company**  
 PD PSL 313-AOS  
 REV. # 4  
 REV. DATE: September 5, 2018

**PSL313-AOS OIL**  
**POLYOLESTER BASED SYNTHETIC LUBRICANT FOR SINTERED METAL BEARINGS**

**DESCRIPTION**

PERMAWICK PSL313-AOS is a Polyolester based synthetic oil providing the ultimate in performance under the most grueling of conditions. Using the highest quality synthetic base stocks along with a sophisticated synergistic additive package, Permawick PSL 313-AOS is specially formulated for a long service life over a wide temperature range.

A flash point of 100 °F higher than conventional mineral oils provide an increased margin of safety. Low pour point and high viscosity index indicate excellent low temperature fluidity and pumpability.

PERMAWICK PSL313-AOS OIL has a proven quality record and is specifically designed to meet the lubricating needs of FHP motor sleeve bearings.

**PRODUCT FEATURES**

- High film strength
- Low evaporation rate and oxidation resistant
- Very shear stable
- Resists rate of change of viscosity with temperature change
- Excellent anti-sludge and anti-varnish characteristics
- Wide temperature range: -40°F to 300°F (-40°C to 150°C)

<b><u>Performance Test</u></b>	<b><u>ASTM Method</u></b>	<b><u>Typicals</u></b>
Gravity, API	D1298	11.4
Specific Gravity	D1298	1.01
Color	D1500	1 – 2
Flash Point, °C	D92	240
Fire Point, °C	D92	310
Pour Point, °C	D97	-54
Viscosity, cSt.	D445	40°C
		60
Viscosity, SUS	D445	100°C
		11.5
		100°F
Viscosity Index	D2270	279
		65
Neutralization No., mg KOH/gm	D664	187
Copper Strip Corrosion		<2
3 hours @ 212°F	D130	1a
Evaporation Loss, wt%		
22 hours @ 210°F	D972	0.15

**The World Leader in Fractional Horsepower Motor Lubrication**

**Permawick Product Data Sheet**