



Permawick Company
 3110 Permawick Drive, Columbus, Indiana 47201
 Phone: 812-376-0703 • Fax: 812-372-1410
 sales@permawick.com
 www.permawick.com

PD P2AO930SG
 REV. #1
 REV. DATE: February 1, 2021

P2AO930SG
PAO Based Synthetic Grease for Electrical Motors

Features

- High film strength – enables sintered bearings to carry heavier loads
- Wide temperature range (-50°C to +120°C)
- High Quality Polyalphaolefins = Excellent temperature stability and low evaporation characteristics
- High viscosity index resists temperature changes

Applications

Gear trains, sliding surfaces, bearings

<u>Grease Performance Test</u>	<u>Method</u>	<u>Typical</u>
Base Oil		Polyalphaolefins
Thickener		Lithium
Penetration (60 strokes, 25°C)	D217	NLGI #1
Color	Visual	Tan, Translucent
Oil Separation, 24 hrs @ 100°C	D6184	<5.0%
Dropping Point, °C	D2265	>200
Density		0.85
Copper Corrosion @ 100°C	D130	1A
Pounds/Gallon		7.10
Structure		Homogenous

<u>BASE Oil FEATURES</u>	<u>METHOD</u>	<u>Typical</u>
Specific Gravity, 15.5°C	D1298	0.85
Color	D150	Clear to straw
Flash Point, °C	D92	>300
Pour Point, °C	D97	-50
Viscosity, cSt	D445	
40°C		202
100°C		24.5
Viscosity Index	D2270	151
Neutralization No.,mg KOH/g	D664	<0.5
Copper Strip Corrosion	D130	
3 hours @ 100°C		1A
Evaporation Loss, wt% 22hrs, 98.9°C	D972	<0.1

The World Leader in Fractional Horsepower Motor Lubrication